

BOOK

The paper has a smooth, fine surface and is appreciated by both end users and printers. Holmen BOOK feels and breathes quality and has been on the market since 2003.

TECHNICAL DATA

Target values subject to production variations. Updates will be done continuously.

Target value	Grammage g/m ²	Brightness % ISO	Bulk cm ³ /g	*Caliper μ m to calculate the book-spine	Opacity %
Holmen BOOK	49	74	1.6	76	94
	52	74	1.6	81	94
	52	74	1.8	90	94
	55	74	1.8	96	95
	55	74	2.0	106	95
	60	74	2.0	116	96
	70	74	2.0	136	97
Holmen BOOK Cream	52	73.5	1.6	81	89
	60	73.5	1.6	92	91
	70	73.5	1.6	108	93
	80	73.5	1.6	123	95
	60	73.5	1.8	104	91
	70	73.5	1.8	122	93
	80	73.5	1.8	140	95
	**49	73.5	2.0	95	89
	52	73.5	2.0	101	90
	55	73.5	2.0	107	91
	60	73.5	2.0	116	92
	70	73.5	2.0	136	93
	80	73.5	2.0	154	95
	**90	73.5	2.0	174	96
	65	73.5	2.2	138	92
Holmen BOOK Bulky	50	58	2.3	109	93
	52	58	2.3	114	93
		Brightness % D65/10°			
Holmen BOOK Extra	65	80	2.0	125	95
	80	80	2.0	154	96
	**90	80	2,0	174	97
Holmen BOOK Extra Cream	**70	80	2.0	136	93
	**80	80	2,0	154	95
Holmen BOOK Extra White	70	80	1.6	108	97
	**80	80	1.6	123	98

BOOK

	Grammage g/m	Whiteness % CIE(W)	Bulk cm ³ /g	*Caliper μ m to calculate the book-spine	Opacity %
Holmen BOOK Fine	52	100	1.5	73	90
	55	100	1.5	77	91
	60	100	1.5	85	93
	**65	100	1.4	88	94
	**70	100	1.4	95	94
Brightness % D65/10°					
Holmen BOOK Fine Cream	**52	80	1.5	73	88
	**55	80	1.5	77	89
	**60	80	1.5	84	91
	**65	80	1.4	88	92

Printing methods: Heatset, Coldset and Digital Inkjet.

* 10-Sheet measurement

** Available depending on trim.

Environment ISO 14001, FSC® C020071, PEFC™ /05-33-134 and EU Ecolabel, Reach.

Updated 2021-05-04