

# BOOK

The paper has a smooth, fine surface and is appreciated by both end users and printers. Holmen BOOK feels and breathes quality and has been on the market since 2003.

## TECHNICAL DATA

Target values subject to production variations. Updates will be done continuously.

Target value	Grammage g/m <sup>2</sup>	Brightness % ISO	Bulk cm <sup>3</sup> /g	*Caliper $\mu$ m to calculate the book-spine	Opacity %
<b>Holmen BOOK</b>	49	74	1.6	76	94
	52	74	1.6	81	94
	52	74	1.8	90	94
	55	74	1.8	96	95
	55	74	2.0	106	95
	60	74	2.0	116	96
	70	74	2.0	136	97
<b>Holmen BOOK Cream</b>	52	73.5	1.6	81	89
	60	73.5	1.6	92	91
	70	73.5	1.6	108	93
	80	73.5	1.6	123	95
	60	73.5	1.8	104	91
	70	73.5	1.8	122	93
	80	73.5	1.8	140	95
	52	73.5	2.0	101	90
	55	73.5	2.0	107	91
	60	73.5	2.0	116	92
	70	73.5	2.0	136	93
	80	73.5	2.0	154	95
	**90	73.5	2.0	174	96
	**65	73.5	2.2	138	92
<b>Holmen BOOK Bulky</b>	52	58	2.3	114	93
		<b>Brightness % D65/10°</b>			
<b>Holmen BOOK Extra</b>	65	80	2.0	125	95
	80	80	2.0	154	96
	**90	80	2.0	174	97
<b>Holmen BOOK Extra Cream</b>	**70	80	2.0	136	93
	**80	80	2.0	154	95
<b>Holmen BOOK Extra White</b>	70	80	1.6	108	97
	**80	80	1.6	123	98

# BOOK

The paper has a smooth, fine surface and is appreciated by both end users and printers. Holmen BOOK feels and breathes quality and has been on the market since 2003.

	<b>Grammage g/m</b>	<b>Whiteness % CIE(W)</b>	<b>Bulk cm<sup>3</sup>/g</b>	<b>*Caliper <math>\mu</math>m to calculate the book-spine</b>	<b>Opacity %</b>
<b>Holmen BOOK Fine</b>	52	100	1.5	73	90
	55	100	1.5	77	91
	60	100	1.5	85	93
	**65	100	1.4	88	94
<b>Brightness % D65/10°</b>					
<b>Holmen BOOK Fine Cream</b>	**52	80	1.5	73	88
	**55	80	1.5	77	89
	**60	80	1.5	84	91

**Printing methods:** Heatset, Coldset and Digital Inkjet.

\* 10-Sheet measurement

\*\* Available depending on trim.

**Environment** ISO 14001, FSC® C020071, PEFC™ /05-33-134 and EU Ecolabel, Reach.

Updated 2020-05-08